

Forms & Guise -



PENTAGONO



Forms & Guise

REPORT CERTIFIED PAINTING HANDLES







Scratch resistance (UNI EN ISO 1518)

Corrosion resistance (UNI EN ISO 9227)

Moisture resistance (UNI EN ISO 6270)

Cross-cutting and adhesion test (UNI EN ISO 2409)

Coating thickness measurement (UNI EN ISO 2178)

Surface hardness measurement with pencil (UNI EN ISO 15184)

MATERIA PRIMA - RAW MATERIAL

Cu %	Pb %	Sn %	Ni %	Fe %	Al %	Mn %	Si %	Zn %
>58	2.1-2,8	<1	<1	<1	Al % 0.4-0.8	< 0.3	< 0,05	resto

BARRA OTTONE - BRASS: CuZn40Pb2-CW617N

PANI OTTONE - BRASS: CuZn37Pb2-CW606N5S

Cu %	Pb%	Sn %	Ni %	Fe %	Al % < 0.05	Mn %	Si %	Zn %	1
57-59	1.6-2.5	< 0,3	< 0,3	< 0,3	< 0.05		Tot. < 0,2		ı

ACCIAIO INOX - STAINLESS STEEL: : AISI 304

Cr%	Ni %	C %	Mn %	Si %	5 %	P%
Cr % 18-20	8-11	< 0.08	< 2	< 0.75	< 0,3	< 0.04

LEGA DI ZINCO - ZINC ALLOY : ZnAl4 (ZL0400) - ZAMAK 13

Zn %	AI %	Cu %	Fe %	Mg %
>95	3,8-4,2	< 0,03	< 0,02	0,035-0,06